

<p>87-331847/47 A96 D21 NIBI-08.04.86 NIPPON BIOCHEM KK 'J6 2238-209-A 08.04.86-JP-079130 (19.10.87) A611-13/18 A61k.07 Mfg. spongy cosmetic material for skin care - from moulded chitosan which is then acylated and impregnated with polymer CB7-141708</p>	<p>A(10-E9, 10-E17, 12-V4) D(8-B9A)</p>
<p>Chitosan with a deacetylation ratio of 40-100% is moulded into the form of sponge, and the moulded chitosan is acylated. The acylation is a chemical modification of the amino gpa. of the chitosan with a 1-2C acid./unsaid, fatty acid and/or a 2-3C decarboxylic acid with an acylation rate of 30-100%. After the acylation, the material is impregnated with a water-soluble high polymer and/or a surfactant. The chitosan is a mixt of chitosan and 5-50 wt% collagen. USE/ADVANTAGE - For providing a spongy cosmetic material with good moisture retention, good flexibility, good biocompatibility, etc. (app Dwg No 0/1)</p>	

DERWENT PURIFICATIONS LTD